

Brandywine Prime™

60# Glossy Inkjet, FSC® Certified / AT-2060 / 40# SC

FACESTOCK DESCRIPTION: 60# Glossy Inkjet, FSC® Certified

Inkjet photo quality paper with a glossy finish. This inkjet paper has excellent water fastness properties. This paper is FSC® certified.

Basis Weight (25 x 38 / 500), lbs.	58.8
Caliper, mils	4.1
Gloss 60°, %	45
Opacity, %	88
Sheffield Smoothness	115
CIE Whiteness	(fs) 155 ± 3
Regulatory Compliance	California Proposition 65, FSC® is a
	voluntary program, and not legally required to
	be adhered to, REACH, RoHS

Avoid exposure to ozone, exhaust fumes or solvent vapors as the absorptive nature of the print receptive topcoat could result in discoloration.



The mark of responsible forestry

ADHESIVE DESCRIPTION: AT-2060

An aggressive all-temperature emulsion acrylic permanent adhesive with good room temperature and excellent cold temperature performance. Exhibits high initial tack and adhesion, even on most textured and hard-to-label substrates, including corrugated. Designed with good die-cuting and stripping properties.

Туре	All-Temperature Permanent
Classification	Emulsion Acrylic
Minimum Application Temp., °F	-20
Service Temperature Range, °F	-65 to +200
Regulatory Compliance	Acute Oral Toxicity 16 CFR 1500.3, ASTM F963 Child Toy Safety, California Proposition 65, CONEG, CPSIA, FDA 21 CFR 175.105, Natural Rubber Latex Free, Primary Eye Irritant 16 CFR 1500.42, Primary Skin Irritant 16 CFR 1500.41, REACH, RoHS, RoHS 2/3

LINER DESCRIPTION: 40# SC

A supercalendered bleached liner. Superior die-cutting and stripping properties. Recommended for rollto-roll applications. Good back printability.

Basis Weight (25 x 38 / 500), lbs	44.7
Caliper, mils	2.5
Brightness, %	78
Gloss, 75°, %	48
Opacity, %	65
Tear, MD / CD, g	32 / 34
Tensile, MD / CD, lbs.	34 /22
Regulatory Compliance	ASTM F963 Child Toy Safety, CONEG, RoHS, REACH

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.